ANUPAM COLOURS & CHEMICALS INDUSTRIES Head Office: 101-102, Kaveri Complex, Jagannath Mandir Road, Sakinaka Junction, Mumbai - 400 072

a Office: 101-102, Kaven Complex, Jagannath Mandir Koad, Sakinaka Junction, Mumbai - 400 072 Phone: :+91-22-2850 6586, 2850 6532 Fax:+91-22-2852 5954 Website: www.anupamcoloursacci.com E-mail: info@anupamcoloursacci.com

ANUCHROME "LEMON CHROME" L-24

ANUCHROME Lemon Chrome L-24 is a monoclinic Lead Chromate material, also known as Pre-Darkened Lemon Chrome. This pigment is highly stabilized and is of very good light fastness and exterior durability.

Therefore, it is suitable for high grade automotive coatings meant for refinishing purposes. It possesses good resistance to acidic and alkaline environment.

Colour Index No.	77603						
Colour Index Pigment No.	Y-34						
Oil Absorption	16-21						
Specific Gravity	4.9-6.0						
Bulk Density g/cc	0.76						
BLEEDING IN (1-Poor 5-Excellent)							
Water	5						
5% Caustic Soda	3						
5% Hydrochloric Acid	3						
Linseed Oil	5						
Ethanol	5						
Ethyl Acetate	5						
Xylene	5						
n-Butanol	5						
Methyl Ethyl Ketone	5						
Mineral Turpentine	5						
Cellosolve	5						
Dioctyl Phthalate	5						
RESISTANCE TO							
120°C / 30 min.	SB						
150°C / 20 min.	SB						
180°C / 10 min.	USB						
210°C / 10 min.	USB						
RESISTANCE TO I	LIGHT						
Full Tone	7						
Tint Tone (1:10)	7						
RESISTANCE	го						
Acid	G						
Alkali	Р						
APPLICATION	-						
Paints	*						
Printing Inks	*						
Rubber	*						
Leather Pastes	*						
Linoleum	*						
PVC Leather Cloth	*						
Paper Coating *							
Chalk / Crayons							
Plastics	*						

TECHNICAL DATA

LEGEND

COLOUR	BLEEDING	HEAT STABILITY	LIGHTFASTNESS	APPLICATIONS	E – EXCELLENT	
Y – YELLOW	SCALE (1-5)	SB : STABLE	SCALE (1-8)	* :RECOMMENDED/	VG – VERY GOOD	
R – RED	5:NO BLEED	USB : UNSTABLE	1 – POOR	MAYBE USED	G – GOOD	
W – WHITE	1:CONSIDERABLE BLEED		8 – EXCELLENT	F – FAIR		
					P – POOR	